

WIRE MANUFACTURERS EST. 1720

Head Office

Webster & Horsfall Limited Hay Mills, Birmingham B25 8DW West Midlands, United Kingdom

Tel: +44 (0)121 772 2555 Fax: +44 (0)121 766 5816

E-mail: sales@websterandhorsfall.co.uk www.websterandhorsfall.com

Sales Office

Tel: +44 (0)121 772 9797 Fax: +44 (0)121 766 5816

STAINLESS STEEL WIRES (AUSTENITIC)

Applications	Corrosion resistant mechanical springs, extension, compression and tension.		
Standards	EN 10270-3 BS 2056 NF A35-587 DIN 17224 ASTM A313+A580	European Great Britain France German USA	Grade: 302, 316, 316, 321
Production Range	0.1mm - 9.5mm (Type 302) 0.1mm - 4.0mm (Type 316 + 321)		
Tensile range	695 N/mm2 – 2600 N/mm2		
Surface	Phosphate coated (plain) Wet drawn Linished Degreased		 Dry drawn wire with soap lubricants Oil drawn polished finish Mechanically ground polish finish Chemically degreased/desoaped (in coil only)
Shaped	The above can also be supplied in shaped wire. (Please see separate sheet)		
Packaging	Catchweight coils, Reels/spools (plastic), Metal reels (up to 300 kgs), Formers, Cut lengths, Specific coil weights/sizes etc. (Please see separate sheet)		

- -Minimal Surface Roughness
- Clean Finish
- Food Contract Safe
- Different Levels of Brightness
- Excellent Cast Helix Control
- - Customer Specific Tensile and Sizes

